



## S33/SIS HYBRID

... one system meeting two  
abrasion standards

### EASY APPLICATION

- + Highest abrasion resistance against sandpaper and also falling sand method
- + Abrasion resistance to be adjusted by the amount of application
- + Roller application on all common machines
- + Designed for almost all substrates and technologies (in combination with the suitable primer)
- + Economic as no extra materials have to be put on stock

### TECHNICAL PROPERTIES

- + Abrasion class >AC2 acc. to DIN EN 13329
- + High transparency
- + Very good coin test > 30 Newton (Hamberger planer)
- + High mechanical resistance @ considerably low g/m<sup>2</sup>

### ADDED VALUE

- + Highly wear-and tear resistant surface, meeting abrasion classes applicable for commercial use

	Premium (standard)	Premium Hybrid	Economy (standard)	Economy Hybrid
Hydro UV Primer	6 g/m <sup>2</sup>	6 g/m <sup>2</sup>	6 g/m <sup>2</sup>	6 g/m <sup>2</sup>
UV Sealer Premium S33/SIS Hybrid		2x 22 g/m <sup>2</sup>		
UV Sealer Economy S33/SIS Hybrid				2x 22 g/m <sup>2</sup>
UV Sealer Premium SIS	3x 22 g/m <sup>2</sup>	1x 22 g/m <sup>2</sup>		
UV Sealer Economy SIS			3x 22 g/m <sup>2</sup>	1x 22 g/m <sup>2</sup>
UV Top Coat	2x 6 g/m <sup>2</sup>	2x 6 g/m <sup>2</sup>	2x 6 g/m <sup>2</sup>	2x 6 g/m <sup>2</sup>
<b>Abrasion SIS (Treibacher sand)</b>	IP 4300 revolutions	IP 4300 revolutions	IP 3800 revolutions	IP 3800 revolutions
<b>Abrasion S33 (change after 500 revolutions)</b>	IP 100 revolutions	IP 800 revolutions	IP 100 revolutions	IP 700 revolutions